

Odporność spryskiwaczy Colad na substancje chemiczne

Substancja	Pojemnik	Uszczelki	
	PP	Colad spryskiwacz ciśnieniowy 9705/9705Z FKM (Viton)	Colad spryskiwacz ciśnieniowy EPDM 9705EPDM
2			
2-ethyl-1-hexanol (isooctanol)	A	A	A
A			
Acetic acid (glacial) concentrated	A	C	A
Acetone	A	C	A
Acetophenone	A	C	A
Acetylacetone	X	C	A
Acetylen, ethene	C	A	A
Alums	A	A	A
Amyl acetate	B	C	A
Amyl alcohol	A	A	A
Aqua regia	B	A	B
Aromat. fuels 50% (fuel C)	X	A	C
B			
Benzaldehyde	A	C	A
Benzene	B	A	C
Benzyl alcohol	A	A	A
Benzyl benzoate	A	A	C
Brake fluid	A	C	A
Butanol (butyl alcohol)	A	A	A
Butanone (methyl ethyl ketone, MEK)	A	C	A
Butyl acetate	B	C	A
Butyl glycol	A	C	A
C			
Calcium hydroxide	A	A	A

A = odporny B = warunkowo odporny C = nieodporny X = nieznaną odporność

Calcium hypochlorite	A	A	A
Castor oil A371	A	A	A
Citric acid	A	A	A
Cyclohexane	A	A	C
Cyclohexanol	A	A	C
Cyclohexanone	A	C	A

D			
Denatured alcohol	X	A	A
Detergent dissolved in water	A	A	A
Diacetanalkohl (diacetone)	X	C	A
Dibutyl ether	B	C	A

Dibutylphthalate (palatinol C)	A	B	A
Dichloromethane (methylene chloride)	X	A	C
Diesel fuel	A	A	C
Diethylene glycol	X	A	A
Dimethylphthalat	X	A	A
Diphenyl (biphenyl)	X	A	C

E			
Ethanol (ethyl alcohol)	A	B	A
Ethanolamine	X	C	A
Ethyl acetate	A/B	C	A
Ethyl chloride	B	A	A
Ethylbenzene	B	A	A
Ethylene glycol (glycol)	A	A	A

F			
Formaldehyde	A	C	A
Furan	X	C	C
Furfuryl alcohol	A	C	S

G			
Glacial acetic acid (acetic acid 100%)	A	C	A
Glycerol	A	A	A
Glycol (ethylene glycol)	A	A	A

H			
Heating oil	A	A	C
Hydraulic oil (mineral oil-based)	C	A	C
Hydrochloric acid for 3-molar concentrated	A	A	A
Hydrofluoric acid <65% cold	X	A	B
> 65% cold	X	A	S
< 65% hot	X	B	B
> 65% hot	X	B	C
Hydrogen fluoride (hydrofluoric acid, anhydro)	A	C	S
Hydrogen peroxide 90%	C	A	B
Hydrogen peroxide diluted	A	A	A
Hypochlorite 12.5%	A/B	A	A

I			
Isobutyl alcohol (isobutanol)	A	A	A
Isocetane	A	A	C
Isopropanol (isopropyl alcohol)	A	A	A

J			
K			
Kerosene	B	A	C

L			
Lavender oil	X	A	C
Linoleic acid	X	A	C
Linseed oil	A	A	B

M			
Methanol	X	C	A
Methanol	A	C	A
Methyl butyl ketone	X	C	A

Methyl ethyl ketone (butanone, MEK)	X	C	A
Methyl formate	A	C	A
Methyl isobutyl ketone (MIBK)	X	C	B
Methyl methacrylate	C	C	C
Mineral oils	A	A	C

N			
Naphtha	A	A	C
Naphthalene	A	A	C
Neatsfoot oil	X	A	A
n-heptane	B	A	C
n-hexane	A	A	C
Nitric acid 3-molar concentrated	A	A	A
Nitrobenzene	C	A	C
Nitromethane	A	A	C
Nitrotoluene	X	A	A
	X	B	C

O			
Olive oil	A	A	A
Oxalic acid	A	A	A
Ozone	A	A	A

P			
Paint solvents	X	C	C
Paint thinner	X	A	C
Paints	X	A	C
Perchloric acid, 2-molar	B	A	A
Petrol	B	A	C
Petroleum	B	A	C
Phenyl ethyl ether	X	C	C
Phosphoric acid 3-molar	A	A	A
Pine oil	A	A	C
Potassium hydroxide 50%	C	C	A
Potassium hydroxide solutions (diluted)	C	A	A
Propane		A	C
Propanol	A	A	A

Q			
R			
S			
Silicone oils	B	X	A
Soda (sodium carbonate)	X	A	A
Sodium hydroxide (caustic soda) 3-molar	A	A	A
Sodium hypochlorite	A	A	B
Sulfuric acid 3-molar	A	A	A
concentrated	A	A	C
Sulfurous acid	A	A	A
Super gasoline	X	A	C
T			
Terpineol	C	A	B
Tetrahydrofuran	B	C	A
Toluene A568	B	A	C
Transformer oil	A	A	C
Transmission oil	X	A	C
Triethanolamine	X	C	A
Trinitrotoluene	X	A	C
Turpentine	X	A	C
U			
V			
Vinegar (5% aqueous acetic acid)	A	A	A
W			
White oil	X	A	C
X			
Xylene	C	A	C
Y			